



# EZ 22- ACS ACRYLIC CURING AND SEALING COMPOUND

## PRODUCT DATA SHEET

623 Chatsworth Hwy 225

Calhoun, GA 30701

706.403.3286

[lamininindustries.com](http://lamininindustries.com)

### DESCRIPTION

EZ 22-ACS Acrylic Curing and Sealing Compound is a clear, transparent, ready-to-apply, non-yellowing liquid compound formulated from special acrylic polymers and quick-evaporating solvents that effectively cures and seals freshly placed concrete.

Once properly applied, EZ 22-ACS provides a premium-grade film for optimum moisture retention. This produces a hard, dense, high-compressive strength concrete. EZ 22-ACS will minimize hair-checking as well as premature cracking, dusting, spalling, and other common defects that result when concrete is not properly cured. This easy-to-use compound dries quickly and protects the concrete during construction. It resists adhesion of mortar droppings and permits easier cleanup.

### USES

EZ 22-ACS is ideal for application on commercial and industrial concrete surfaces, sidewalks, patios, multi-level parking decks, driveways, and parking areas ... wherever you want to simultaneously cure and seal exterior concrete surfaces. The use of EZ 22-ACS on any exterior concrete surface provides a durable, long-lasting finish that offers improved resistance to chemicals, oil, grease, deicing salts, and abrasion. EZ 22-ACS provides an attractive, low-sheen finish that enhances the natural appearance of the concrete.

### SPECIFICATIONS

- Complies with U.S. EPA maximum allowable VOC requirements.

### LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

### PACKAGING

1 Gallon (3.79 Liter) Cans (6 per case)

5 Gallon (18.93 Liter) Pails

55 Gallon (208.20 Liter) Drums

### FEATURES/BENEFITS

- Provides a totally clear membrane for new or existing concrete that will not yellow.
- Provides a tough, durable, uniform, long-lasting film on exterior concrete surfaces.
- Cures and seals freshly placed concrete simultaneously in one application.
- Produces a premium-grade seal, yielding optimum moisture retention.
- Minimizes hair checking, cracking, dusting, spalling, and other defects common to uncured or improperly cured concrete.
- Provides improved resistance to chemicals, oil, grease, deicing salts, and abrasion during construction.
- Non-blushing, breathable film.
- Provides an attractive sheen that enhances the natural appearance of concrete.
- Applies easily ... dries quickly for less downtime.
- Permits easy cleanup and housekeeping ... reduces floor maintenance costs.
- VOC compliant.

### SPECIFICATIONS

- ASTM C 309, Type 1, Classes A & B
- ASTM C 1315, Type I, Class A
- AASHTO M 148, Type 1 Classes A & B
- USDA Accepted

### COVERAGE\*

300-600 ft.<sup>2</sup>/gal. (7.37-14.73 m<sup>2</sup>/L)

\*Coverage may vary due to porosity and condition of concrete.



Page 2  
EZ 22-ACS  
ACRYLIC CURING AND SEALING  
COMPOUND  
PRODUCT DATA SHEET

623 Chatsworth Hwy 225

Calhoun, GA 30701

706.403.3286

[lamininindustries.com](http://lamininindustries.com)

## APPLICATION

### Surface Preparation

Existing concrete surface must be clean and dry with all stains, oil, grease, dust, and dirt removed prior to application.

EZ 22-ACS should be applied when surface water has completely disappeared and the concrete surface will not be marred by walking workmen.

### Application Method

Use a sprayer or short-nap roller to apply a uniform film. Avoid puddling in low areas. If puddles occur, brush or roll them out. A standard industrial-grade sprayer, equipped with a neoprene hose and gaskets, as well as a 5941 spray nozzle (or equivalent) is recommended for best results.

For optimum performance, apply first coat at 600 ft. 2/gal. After the first coat has thoroughly dried, apply a second coat at 600 ft. 2/gal.

**Note:** The second coat should be applied at a right angle.

### Drying Time

EZ 22-ACS dries quickly. Drying times may be extended depending on application rate, temperature, humidity, and project conditions. Restrict foot traffic for at least four hours. Twelve hours is preferable.

### Cleanup

Application equipment should be cleaned promptly after use with xylene or toluene.

## PRECAUTIONS

DO NOT DILUTE. FOR EXTERIOR APPLICATION ONLY. Surfaces treated with EZ 22-ACS may become slippery under certain conditions.

EZ 22-ACS should not be applied during high temperature conditions in direct sunlight. These conditions cause rapid evaporation, which does not allow the film to form properly. Under these conditions, the film may peel, bubble, and/or turn white (blush). EZ 22-ACS should not be applied to concrete exposed to excessive moisture. Entrapped moisture in a solvent-based sealer may cause the film to peel and/or turn white (blush).

Do not apply EZ 22-ACS if the temperature of the concrete is below 40° F (4° C). EZ 22-ACS may be used on colored concrete, but mottling may occur. Do not use on dense or non-porous surfaces, i.e. brick, stone, etc.

Concrete containing calcium chloride will remain dark longer when treated with EZ 22-ACS. Concrete floors properly cured with EZ 22-ACS meet section 8.9 "Adhesion of Tile Cements" of ASTM C 1315. For other specifications, secure the approval of the paint or resilient flooring manufacturer before applying EZ 22-ACS. The specifier and user shall determine the suitability of product for specific applications and assume all responsibility in connection therewith.

EZ 22-ACS is a membrane-forming sealer. All membrane-forming sealers may darken concrete or magnify imperfections caused by variations in the porosity and/or finishing of the concrete.

## HEALTH HAZARDS

Prolonged inhalation of vapors in excess of permissible exposure limits may result in symptoms of transient central nervous system depression. Direct contact with the product may result in irritation of the skin and eyes. Product vapors may also cause irritation. **EZ 22-ACS is combustible.** Remove ignition sources prior to use. Empty containers may hold combustible vapors. Handle empty containers as combustible liquids. In the event of a spill, contain the product, apply absorbents and place in sealed containers. In the event of a fire, contain all run-off water. Refer to Material Safety Data Sheet for complete health and safety information.

## DISCLAIMER

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. Laminin Industries cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As Laminin Industries has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

For warranty information, contact your Laminin sales associate.