

COLOSSAL 117-EPS PRIMER AND SEALER

PRODUCT DATA SHEET

623 Chatsworth Hwy 225

Calhoun, GA 30701

)1 706.403.3286

lamininindustries.com

PRODUCT DESCRIPTION

Colossal 117-EPS Primer and Sealer is a 2-component, hybrid-epoxy resin based primer for sub-floor preparation prior to installation of urethane-based leveling compounds. Unlike water or urethane-based primer, Colossal 117 EPS P&S is not affected by elevated subfloor moisture. It will not foam up or get weaker because of water present in the sub-floor. It also has a higher penetration of the concrete compared to traditional 100% solid epoxies, which creates a stronger bond. It does however NOT create a moisture barrier but merely reduces the amount of vapor penetration. Colossal 117 EPS P&S spreads easily and creates a dust free surface ready for safe installation of flooring. It increases the bonding of subsequently applied primers, leveling compounds, and/or adhesives.

PRE-INSTALLATION CHECKLIST

A successful installation requires proper preparation of the sub-floor. Read and understand all applicable guidelines and technical data sheets before installation. Follow industry standards and flooring manufacturer's recommendations for sub-floor moisture content, design, layout and application of flooring materials. Backing of all flooring material must be solid and sound and free of any anti-adherents. All slab constructions must meet the specific requirements of the floor covering to be installed.

SUB FLOOR EXAMINATION

Do not apply sealer onto a visibly damp or wet surface. Examine concrete sub floor for color, cleanliness, porosity and pre-existing residues PRIOR TO installation. Concrete sub-floors must be checked for any contaminants and/or anti-adherents using the Laminin Epoxy Test Kit. Prior to installation, the sub-floor must be checked according to applicable installation guidelines. It must be solid and sound, clean, free of chaps and anti-adherents, as well as resistant to pressure and tension. Check for missing or compromised vapor barriers and hydrostatic pressure. Perform RH or CaCl moisture tests following ASTM standards. Results of 99% RH or 25# CaCl could indicate that there is a higher moisture content in the slab than what tests can measure and there might be hydrostatic pressure and/or a compromised or missing vapor barrier.

SUB FLOOR PREPARATION

The condition of the sub-floor will determine which type of mechanical treatment is required (e.g. wire brushing, sanding, grinding or shot blasting). Dust, paint, curing compounds, sealers, residual adhesives or other surface pollutants MUST be removed by suitable means. Extent of sub-floor preparation can only be determined at the site by the installer. Clean the surface with an industrial vacuum cleaner, tack or damp mop floor before application. Do not use sweeping compounds as most will contain oil or wax which will act as an anti-adherent and prevent primers, sealers, leveling compounds, coatings and/or adhesives from bonding to the concrete. Cracks and gaps must be treated prior to application of primers, sealers, leveling compounds, coatings and/or adhesives.

MIXING OF COMPONENTS

Lid contains hardener. Pierce all the way through plastic disc in center of lid and the bottom of the lid using a long screwdriver or similar tool. Let the hardener flow into the lower part of the bucket for one minute. All of the hardener must drain into the pail before mixing parts A&B. Open ring, remove the lid, and mix both components with mixing paddle for at least 3 minutes. Use an electric drill with less than 300 rpm until an even color is reached. Avoid air entrapment by mixing slowly and using an appropriate mixing paddle. Make sure to mix along wall and bottom-part of the container as well. Temperature of both components should be at least 50 °F before mixing.

INSTALLATION PROCEDURE

Mix pail according to mixing instructions. Apply coating undiluted with approved applicator. Make sure coating is spread evenly and up to the perimeters. The spread rate is critical for a successful installation. Do not exceed the minimum or maximum coverage.

LIMITATIONS

When using other than Laminin Industries products in conjunction with Laminin Industries primers, sealers, leveling compounds, or adhesives, Laminin Industries denies any and all responsibility for any ensuing problems and/or damages without prior written authorization from Laminin Industries. Do not dilute primer/sealer or mix with other products. In case of accident, injury, spill or exposure, see SDS sheet for information. Sealer will not prevent moisture damages from hydrostatic pressure, missing or compromised vapor barriers, underground springs, damaged water pipes, sinks, ice makers, faulty plumbing, flooding, etc. The foregoing representations are based on the results of our most current product and material testing within a controlled environment and are of a non-obligatory advisory nature only. As such, they do not constitute an express or implied warranty of any kind including the Warranty of Merchantability and/or Fitness for a Particular Purpose. Because we have no control over the actual quality of workmanship, materials used and worksite conditions, Laminin Industries USA, LLC. will in no event be liable for any incidental and/or consequential damages. Therefore, we strongly recommend that prior on-site testing be conducted to refer to and study the suitability of the product for the intended purpose. With the release of this technical information sheet all its prior versions become invalid. For warranty and warranty disclaimer information contact your Laminin sales associate.



Page 2 COLOSSAL 117-EPS PRIMER AND SEALER

PRODUCT DATA SHEET

lamininindustries.com

623 Chatsworth Hwy 225

Calhoun, GA 30701

- **GENERAL FEATURES**
 - Leed qualified
 - Works under any type of flooring
 - Contains no isocyanates
 - Contains no chlorinated solvents
 - Contains no solvents
 - Contains no VOC (calc. per CA Rule 1168)
 - High solids content
 - Ozone friendly

INSTALLATION FEATURES

- Creates dust free surface
- Very low odor
- High spread rate
- Excellent penetration of sub floor
- Higher temp & HR will shorten drying time
- Observe pot life during installation

LONG-TERM FEATURES

- Resistant against aging
- Suitable for radiant heat systems

APPROVED SUB-FLOORS

- Concrete Slabs
- Ceramic tiles
- Stone, Terrazzo
- Wet Concrete Slab up to 25# / 24hrs / 1,000SF and 100% RH
- Stained Concretes (well bonded)

APPROVED TROWELS AND SPREAD RATE

 3/8 in. Nap Roller: up to 320 SF/gal (5 mil)

Open Time	30% R/H	50% R/H	80% R/H
50°F/10°C	90 min.	90 min.	90 min.
70ºF/21ºC	75 min.	75 min.	75 min.
90ºF/32ºC	60 min.	60 min.	60 min.

DRYING TIME

Approx. 2 hours or until clear

TEMPERATURE RANGE DURING INSTALLATION

• 50° - 90°F,

RELATIVE HUMIDITY RANGE DURING INSTALLATION

• 30% - 80%

PACKAGING SIZE

- 2-1/2 gal. Metal Combo pail (A+B)
- 60 per pallet
- 0.75 qrt plastic jug Part A + 2.25 qrt plastic jug Part B

DENSITY [LBS./GAL.]

• 8.9

COLOR

• White

COLOR HARDENER

• Whit e

MIXING RATIO

• 1 Part A + 3 Parts B by weight

POT LIFE

• Approx. 45 min @ 70 °F (21 ° C)

PH VALUE OF CONCRETE

Resistent up to 14

STORAGE

706.403.3286

• Above 32° F, not freeze/thaw stable

SHELF LIFE

• 24 months in original, unopened container

TRANSPORTATION

- Above 32° F, not freeze/thaw stable UN
 3082 ENVIRONMENTALLY HAZARDOUS
- SUBSTANCE, LIQUID, N.O.S. (Epoxide
- resin), 9, III